



Timberspecies	Colour Enhancing System			Colour Lightening System			Top Coats				
	Allbase alcohol (indent)	Pall-X 333 Oil 'Primer'	Pall-X 333 Oil 'Colour Seal'	Pall-X 340 waterborne	Pall-X 325 waterborne (indent)	Pall-X 96 waterborne	Pall XExtreme waterborne	Magic Oil oil based	Pall-X 96 1 part	Pall Extreme 1 & 2 part	Pall-X Zero 2 part (indent)
Akwa	●	●	●					●	●	●	●
Beech European	●	●	●	●	●	●	●	●	●	●	●
Brushbox	●	●	●					●	●	●	●
Calophyllum	●	●	●	●		●		●	●	●	●
Douglas Fir		●	●	●	●	●	●	●	●	●	●
Jarrah	●	●	●					●	●	●	●
Jarrah Pacific	●	●	●					●	●	●	●
Karri	●	●	●					●	●	●	●
Kauri		●	●	●	●			●	●	●	●
Kauri Fijian		●	●	●		●		●	●	●	●
Kwila	●	●	●					●	●	●	●
Macrocarpa		●	●	●	●	●	●	●	●	●	●
Maple	●	●	●	●	●	●	●	●	●	●	●
Massa	●	●	●					●	●	●	●
Matai	●*	●	●	●		●		●*	●	●	●
Merbau	●	●	●					●	●	●	●
Oak Red American	●	●	●			●		●	●	●	●
Oak White American	●	●	●		●	●	●	●	●	●	●
Oak European	●	●	●		●	●	●	●	●	●	●
Oak French	● before blondin	●	●		●	●	●	●	●	●	●
Oak Roasted	●	●	●					●	●	●	●
Oak Tasmanian	●	●	●		●	●	●	●	●	●	●
Pine		●	●	●	●	●	●	●	●	●	●
Pine Radiata		●	●	●	●	●	●	●	●	●	●
Purple Heart	●	●	●					●	●	●	●
Rimu	●	●*	●*	●		●		●*	●	●	●
Rimu Pacific	●	●*	●*	●		●		●*	●	●	●
Rosewood	●	●*	●*	●		●		●*	●	●	●
Saligna	●	●	●	●				●	●	●	●
Spotted Gum	●	●	●					●	●	●	●
Taukkyan	●	●	●					●	●	●	●
Taun	●	●	●	●				●	●	●	●
Tawa	●	●	●	●	●	●	●	●	●	●	●
Teak	●	●	●					●	●	●	●
Tonka	●	●	●					●	●	●	●
Victorian Ash	●	●	●		●	●	●	●	●	●	●
Vitex	2x ●	●*	●*					●*	●	●	●
Walnut American	●	●	●					●	●	●	●
Walnut East Indian	●	●	●					●	●	●	●
Wenge	●	●	●					●	●	●	●
Yaka (Pacific Rimu)	●	●	●	●		●		●	●	●	●

- \* Oil may take longer to cure, up to 4 days      ● Softwoods may require 3 coats of Magic Oil
- All tanalised timber (green) may need two coats of Allbase to lock out tannin bleeding.
- Any timber greasy, waxy or with unwanted tannin or colour bleeding issues use 1 or 2 coats of Allbase first
- When coating exotic timber please do a test area first if unsure!!!
- Pall-X 333 'Colour Seal' is an Oil Based colour timber seal system. Please seek technical assistance for information.
- Pall-X 333 'Colour Seal' is available in Standard colours only - Black, White, Brown, Red Brown, Grey.

Timber is a natural product and densities may vary. On existing timber floors there can be contamination from previous treatments or useage. This table has been with our best knowledge and experience. We strongly recommend testing of timber prior to the commencement of the project.

The above information is based on our experience and careful investigations. The variety of associated materials and different construction and working conditions cannot be individually checked or influenced by us. The quality of your work depends, therefore, on your own professional judgement and product usage. If in doubt, conduct a small test or obtain technical advice.