



SAMPLE RECEIVED FROM: Luxe Group Limited

Date: 30.11.18

SAMPLE DESCRIPTION: Black laminate underlay, 11mm/120kg.

1 of 1

ASTM C518-2017 - Steady -State Thermal Transmission Properties by Means of the Heat Flow Apparatus

Note: This test was sub-contracted (test no. 18-007250).

20°C Test Apparatus Used: Lasercomp Fox 600 Temperature Differential: Sample Orientation: Horizontal Estimated Uncertainty in Results: 3.9% Mean Test Temperature: 15°C Heat Flow Direction: Up Average Thermal Gradient: 366.6 K/m

	Specimens	
	1	2
Specimen Thickness (as received) (mm)	11	11
Specimen Thickness (as tested) (mm)	55	55
Specimen Density (as tested) (kg/m³)	25	25
Test Duration (hrs:mins.)	03:29	02:42
Measured Heat Flux (W/m²)	13.6	13.6
Measured Thermal Conductance (W/m²K)	0.0679	0.0680
Measured Thermal Conductivity (W/m.K)	0.0371	0.0371
Thermal Resistance (m²K/W)	1.5	1.5
Thermal Resistance – 1 Layer (m²K/W)	0.29	0.29

The calibration of the Heat Flow Apparatus was checked immediately prior to the commencement of the test.

Group of 5 stacked specimens turned at 90° for second result.

L A Greer Signatory

Signatory

18/12/2018

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED" Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

New Zealand Wool Testing Authority Ltd

22 Bridge Street, PO Box 12065 Ahuriri, Napier 4144, New Zealand

T+64 6 835 1086, F+64 6 835 6473 Email: testing@nzwta.co.nz