



### max seal™ CAULK IN COLOURS

#### Description

max seal™ Caulk in Colours sealant is a flexible, water based acrylic latex joint sealant for use in sealing expansion and other joints in residential construction work and tiling.

#### Pack Size and colours

- CIC Black resource no. 6003354112
- CIC Brilliant white resource no. 7001734112
- CIC Cedar resource no. 6003384112
- CIC Charcoal resource no. 6030974112
- CIC Cream resource no. 6031104112
- CIC Earth resource no. 6030934112
- CIC Fawn resource no. 6030994112
- CIC Light grey resource no.6030924112
- CIC Light ivory resource no 6008324112
- CIC Mocca resource no.6030954112
- CIC Terracotta resource no 6030964112
- CIC Vanilla resource no 6003474112
- CIC Warm brown resource no 6030944112
- CIC white resource no 6003484112

#### Benefits

- Suitable for internal and external use
- Highly elastic +/- 20% movement capability
- Water based, easy to use and clean up
- Available in a variety of decorator and building material colours
- Does not slump or sag in joints up to 15mm wide
- Strong adhesion to all the substrates listed
- Resistant to mould growth
- Water and UV resistant

- Paintable (if required)
- Mould resistant
- Caulk in colours meets the requirements of LEED Certification: Indoor Environmental Quality - Credit 4.1 (Low-Emitting Materials: Adhesives and Sealants). See MSDS for VOC value.

#### Uses

- Sealant in wet areas (not for immersion)
- Filling gaps between baths, basins, shower hobs and tiles.
- Expansion joints in brickwork and tiled walls up to 15mm wide.
- Sealing around architraves, window and door frames.
- Patching up tile grouting.

#### Compatible Substrates

Concrete	Polyurethane foam
Cement sheeting	Plywood
Metal	Particleboard
Plasterboard	Cement render
Timber	Expanded polystyrene

#### Performance Summary

Storage life	24 months unopened
Skinning time	20 minutes
Full cure	3-7 days depending on conditions and thickness
Service temperature	-5°C to 80°C
Specific Gravity	~1.5
Movement capability	+/- 20%

### Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 22225588



**Coverage**

450g cartridge will give approximately 15 lineal meters of a 5mm bead.

**General Application**

Cut tip off plastic nipple. Screw on nozzle and load into cartridge gun. Cut nozzle to desired size. With gentle trigger pressure, dispense sealant into joint. Use a spatula to tool off to desired finish. Allow to dry before coming into contact with water

**Surface Preparation**

All surfaces must be clean, dry, sound and free of dust, oil, old sealant or other contamination.

Lightly contaminated surfaces should be wiped with Isopropyl Alcohol (IPA) using the 2-rag wipe method. Apply IPA to a clean lint-free cloth and wipe onto the surface to be cleaned to solubilise and remove the majority of the contaminant. A clean dry cloth should then be applied to remove remaining contamination and dry the surface. Ensure wet cleaner is not allowed to dry on surface. For more heavily contaminated surfaces or where the IPA does not remove the contaminant, a generic wax and grease remover should be applied using the same 2-rag wipe method. Once this has been completed the surface should be given a final clean with IPA using the 2-rag wipe method to ensure the surface is adequately prepared. Adhesion to metals and some surface finishes can be further improved by light abrasion prior to cleaning with IPA using the 2 rag-wipe method. For glazing applications IPA should be used to clean and prepare the surface. Manufacturers of plastics should be consulted about suitable cleaning solvents. Adhesion to plastics should be pre-tested.

Mask either side of joint to produce a neat finish.

Use a suitable sized foam backing rod or polyethylene bond breaker tape to prevent three sided joint contact impeding the free and even deformation of the sealant in a cyclic joint.

**Expansion Joints**

When used in expansion joints ensure the joint is at least 6mm in depth and no more than 15mm in width. For joints between 6mm and 12mm width maintain the joint depth at 6mm, while for wider joints the ratio of width to depth should be 2:1. Ensure the base of the joint is not directly in contact with the sealant by using tape, foam or backing rod in the joint base."

**Cure Time**

max seal™ Caulk in Colours acrylic sealant will cure in three to seven days depending on joint dimensions, temperature and substrate porosity. The lower the temperature or higher the humidity will result in longer curing times.

**Clean Up**

Clean up uncured sealant with a wet rag and water. Cured material can be removed by trimming with a knife or scraper.

**Safety Information**

max seal™ Caulk in Colours is not classified as hazardous according to criteria of Safe Work Australia. A Material Safety Data Sheet is available from the H.B. Fuller representative your state, HB Fuller Australia customer service, or downloadable from the HB Fuller web site, [www.hbfuller.com.au](http://www.hbfuller.com.au)

**Our Focus is Clear. Perfecting Adhesives.**

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 22225588



**Limitations**

- Not suitable where both surfaces are non porous.
- Not suitable for constant water immersion or where water may pool on surface .e.g. shower bases, paving joints.
- Not suitable for foot or vehicle traffic areas or flooring
- Cannot be stained
- Mould resistance will deteriorate over time, ensure surfaces are cleaned often to prevent build up of contaminants that may support mould growth.

**Disclaimer**

This technical data sheet summarises at the date of issue to the best technical knowledge of HB Fuller Australia. Since HB Fuller Australia cannot anticipate or control the conditions under which the product may be used, each user must, prior to usage, review this technical data sheet in the context of how the user intends to handle and use the product in the workplace. If clarification or further information is needed to ensure that an appropriate assessment can be made, the user should contact this company. Our responsibility for the products sold is subject to our standard terms and conditions, a copy of which is sent to our customers and is also available on request

Version 3  
TDS Date: 21/05/2013

**Our Focus is Clear. Perfecting Adhesives.**

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the **total aggregate liability of H.B. Fuller** for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 2225588

**H.B. Fuller**