

## **TECHNICAL DATA SHEET**

Customer Services CHC : 03 379 7067 or AKL: 09 443 7067 Email: help@giltedge.co.nz Technical & Sales Assistance Email: help@giltedge.co.nz www.giltedge.co.nz

## Feltworx

Nonwoven needle punched carpet underlay 100% Recycled wool and wool rich carpet

PROPERTY	AS 4288	Typical
	Requirements	Result
type		felt
thickness mm		10.0
weightg/m2		1200
Breaking strength		
Length (N/50mm)	40 min	389
Width (N/50mm)	40 min	234
	40 1111	234
Extension at 40N Force		
Length (%)	20 max	2.4
Width (%)	20 max	6.3
Loss of Thickness		
Static loading (%) after 24 hr recovery	40 max	24.9
Dynamic Loading (%)	40 max	17.4
Work of Compression		
Work of Compression (J/m2)		106
Work of Compression (J/m2)after Dynamic Loading	50 min-200 max	86
Retention of Work of Compression after Loading (%)	40 min	81
Deflection at 100kpa after Loading (mm)	1.5 min-9 max	3.0
Thermal Resistance (m <sup>2</sup> K/W) R value	ASTM C518-10	0.28
Acoustic Properties		
Reduction of Impact Sound (dB)	ISO 10140	28
Noise Reduction Coefficient	ISO 354	0.30
Insect Resist treatment		Yes
Anti-bacterial treatment-BioKlenz		Yes
Natural Sanitiser based on citrus extracts		
Classification	AS 4288:2003	Heavy
		Commercial