

Tuesday July 21<sup>st</sup>, 2009

Manufacturer: RLA Polymers Pty Ltd (67 Dalgety Drive, Manukau City Auckland New Zealand 2104)

Sample Description: Polymer 265 carpet adhesive

Date Tested: July 2009 (Tested by FORAY Laboratories - NATA Accreditation 1231)

Test Method: SCAQMD Method 304-91 Determination of Volatile Organic Compounds (VOC) in Various Materials as referenced by South Coast Air Quality Management Division (SCAQMD) Rule 1168.

Test Data:

<b>Specification</b> New Zealand Green Building Council Green Star NZ Office 2009 IEQ-3 Green Star NZ Office Interiors IEQ-3	Polymer 265
Indoor Carpet Adhesive 50 grams per Litre as VOC content material	46 grams per Litre as VOC content material

Dr. Vyt Garnys PhD, BSc(Hons) AIMM, ARACI, ISIAQ ACA, AIRAH, FMA Managing Director and Principal Consultant

F0907-16